

VERSAL RED 2GC


 TiO₂ 1:1

 TiO₂ 1:10

Characteristic

C. I.	Pigment Red 4
CAS No.	2814-77-9
Chemical Class	2-Naphthol

Properties

Oil Absorption [ml/100 g]	48
Density [g/cm ³]	1.5
Bulking Volume [l/kg]	3.8

Fastness

Linseed Oil	4-5
White Spirite	3
DEHT	3-4
Xylene	2
Acetone	2-3
Butylacetate	2-3
Ethanol	3-4
Water	5
HCl 2.5%	5
NaOH 2.5%	5
Light - Full Shade	6
Light - 1/1	5-6
Light - 1/3	3
Weather - Full Shade	2-3
Weather - 1/1	2
Weather - 1/3	1-2
Overspray	2-3
Heat Resistance [°C]	C 140
Migration	

C - in Coatings

Application Possibilities

Printing Inks - Nitrocellulose	●
Printing Inks - Waterbased	●
Printing Inks - Offset	○
● main application	○ side application

Other Informations

Shelf Life	48 months
------------	-----------

Testing methods

Density

- determined by ČSN EN ISO 787-10: 1997 (67 0520) in $v \text{ g/cm}^3$

Bulking Volume

- denotes the volume of 1 kg of loosely poured pigment, expressed in litres

Oil Absorbtion

- determined by ČSN EN ISO 787-5: 1997 (67 0520) in ml/100 g pigment

Fastness to Solvents

- colouring of solvent after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one

Fastness to Reagents

- colouring of reagents after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one

Light Fastness - Xenotest

- determined by ČSN EN ISO 105-B02: 2000 (80 0147) and evaluated in 1/3 and 1/1 of standard depth and in full shade; determined according to blue scale, by it degree 1 denotes the lowest fastness, degree 8 the highest one

Weathering Fastness - Xenotest

- determined by ČSN EN ISO 105-B04: 1998 (80 0171) and evaluated in 1/3 and 1/1 of standard depth and in full shade; determined according to grey scale, by it degree 1 denotes the lowest fastness, degree 5 the highest one

Overspray Fastness

- assessment of bleeding into a white nitrocellulose combination lacquer for 60 min. at 70 °C against ISO grey scale; by it degree 1 denotes the lowest fastness, degree 5 the highest one

Heat Resistance

- the values quoted indicate up to what temperature the pigments do not significantly alter; these are guide values which can be influenced by the binder used and the period of exposure to high temperature

Migration Fastness

- assessment of bleeding into a white polyvinylchloride sheet for 24 h at 70 °C against ISO grey scale; by it degree 1 denotes the lowest fastness, degree 5 the highest one; no data means that the pigment is not recommended for dyeing of PVC

Fastness to plasticizers

- colouring of plasticizer (diethylhexylterephthalate) after 24 h at 20 °C according to ISO grey scale is determined; degree 1 denotes the lowest fastness, degree 5 the highest one